

# :: Primer Spray

primer

# **CHARACTERISTICS**

Primer Spray provides a fast-drying, alkyd resin-based adhesive base and has excellent anti-rust properties. This product has a strong passivation effect because it contains zinc phosphate.

### **APPLICATION**

Primer Spray is used as a primer for steel, iron, and cast iron surfaces. For pre-treatment of substrates prior to painting. Base primer for dark paint colors. Test the product first if you plan to paint using two-component materials.

### **PRODUCT DATA**

Material data: Color: red-brown

Solids by volume: 65 - 70 % Drying time (20°C): 30 minutes Dust-dry (20°C): 10 minutes Recoat time (20°C): 3-6 hours

Hardened in (20°C): Approx. 12 hours

#### **HANDLING**

The surfaces to be primed must be clean, dry, and free of rust, grease and oil. Metal surfaces should be sandblasted in accordance with SA 2 1/2. Shake the can well for at least 2-3 minutes before use. Spray from approx. 25-30 cm (10-12 in) away from the surface. Apply thin coats in steady, even up-and-down and side-to-side movements.





## **SAFETY ISSUES**

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply. Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE

Telefon Telefax E-Mail +49 (0) 4122/717 -0 +49 (0) 4122/717-158 info@vosschemie.de